



## COLLECTION | SIGNATURE COLOR | RAW SIENNA

Wood species | Oak  
Grade | Character  
Constructions | 3-layer T&G Engineered Flooring  
Size | 19,05 x 190 x 600...2100 mm (¾" x 7 ½" x 2'..7")  
Finish | Silk Oil ultra matte

### CONSTRUCTION : 3-LAYER T&G ENGINEERED FLOORING

DIMENSIONS :			PACKAGING :		
			BOX	PALLET	
Thickness	19,05 mm (¾")		Content:	1,86m <sup>2</sup>	40 (74,4 m <sup>2</sup> )
Width	190 mm (7 ½)		Weight	23 kg	950 kg
Length	600 ...2100 mm (2'..7')		H x W x L	95 x 225 x 2150 mm	1120 x 905 x 2160 mm
Average length	1,22 m (4')		Content:	20,01 sq.ft.	800,40 sq.ft.
Microbevel	0,5 mm		Weight	51 lb	2100 lb
Joint type	tongue and groove (T&G)	H x W x L	4" x 10" x 85"	44" x 36" x 85"	

### DEVIATIONS :

Deviation on Thickness	± 0,2 mm	EN 13489
Deviation on Width	± 0,2 mm	
Height Difference	≤ 0,2 % of width	ГОСТ 862.3
Cup	≤ 0,2 % of plank width	CT5 2121
Bow	≤ 0,1 % of length	EN 13489
Spring	≤ 0,5 % of length	

### CHARACTERISTICS :

Fire resistance	Dfl-s1	EN 14342
Formaldehyde emission class	E1	
Pentachlorophenol content	None	
Thermal resistance	0,118 m <sup>2</sup> ·K/W	
Thermal conductivity	0,161 W/(m·K)	
Structural warranty	Lifetime	

### INSTALLATION :



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

### STORAGE AND USAGE :



— Air humidity 40% – 65%  
— Temperature +18 °C – +22 °C

### FINISH : SILK OIL ULTRA MATTE

DESCRIPTION :	
Type of coating	UV-cured modified polyurethane-acrylate
Surface (finish) type	Semi-closed pores, wire brushed
Sheen	Matte 2-7 GU/60°
Finish warranty	-

### CLASSIFICATION SURFACE CHARACTERISTICS :

Wear resistance	Not rated	EN 438-2
Scratch resistance	Not rated	EN 438
Slip resistance	50 (SRV dry)	EN 15676
Resistance to chemical agents	Class 5 (Except blue ink)	EN 13442
Repairability	Medium	

### MAINTENANCE AND CARE CONDITIONS :

Maintenance of hardwood floors with Silk Oil finish assumes regular (daily if necessary) cleaning from dust and grit using a vacuum, followed by a thorough cleaning with Coswick Hardwood Floor Cleaner or other similar product. Floor surface areas that receive the most traffic and get worn down quicker, such as areas by the front door, hallways, kitchens etc., should be periodically renewed with special Coswick Restorative Oil. This product restores the protective surface film. Frequency of use depends on type of interior and intensity of foot traffic. For residential interiors, restorative cleaning should be done once in 3-5 years; for public and commercial interiors with intense foot traffic, it is recommended to use the product 2-4 times a year.

### GRADE : CHARACTER

DESCRIPTION :		DESCRIPTION :	
Sound sapwood	No limit	Bark pocket	No limit (after filling)
Colour variation	No limit	Pith	Permitted
Knot	No limit (after filling)	Slope of grain	Permitted
Checks	Permitted filled up to 3 mm in width	Medullary ray	Permitted